

TYTAN PROFESSIONAL - Super Glue RB-20

One-component mounting adhesive based on synthetic rubber in organic solvents. Adhesive is used for various assembly and finishing works in construction.

APPLICATIONS

| for bonding of wide range of building |
|--|
| materials to most typical surfaces, such |
| as: concrete, plaster, chipboard, wood, |
| plaster board, brick |
| bonding of baseboards, plinths, doorsteps, |
| floor panels, ceramic tiles. |
| bonding decorative elements made of |
| wood, gypsum, cork, chipboard, metal, |
| stones, foamed polystyrene |
| bonding of mineral and glass wool |
| clamping of carpets and PVC floor |
| coverings |

BENEFITS

| fast and durable initial tack |
|-------------------------------|
| flexible joint |
| high final strength |
| excellent adhesion |
| moisture resistant |

APPLICATION CONDITIONS

| Application temperature [°C] | +10 - +30 |
|-----------------------------------|-----------|
| Optimal bonding temperature [°C] | +15 - +20 |
| Optimal relative air humidity [%] | 60 |

DIRECTIONS FOR USE

Prior to application, read safety instruction presented in MSDS.

1. SURFACE PREPARATION

• Bonded surfaces must be level, dry, free from contaminations and substances hindering adhesion.

2. PRODUCT PREPARATION

• Cut the nozzle to the required diameter, cut the cartridge outlet and screw the nozzle. Insert the cartridge into the applicator gun.

3. APPLICATION

Apply adhesive in spots or strips on the surface or bonded material.

2014.08.08



Selena FM S.A. ul. Strzegomska 2-4, 53-611 Wrocław, Poland, tel. +48 71 78 38 290, fax: +48 71 78 38 291 e-mail: export@selena.com, www.selenafm.com



- Immediately join the surfaces firmly together with a little twist motion, disconnect them, wait 3-5 minutes and press again strongly and evenly.
- Element's position can be easily corrected without disconnecting for 2-3 minutes after connection.

4. WORKS AFTER COMPLETION OF APPLICATION

- Cleaning: before curing acetone or mineral spirits, after curing mechanically.
- DO NOT WASH HANDS WITH SOLVENTS.

5. REMARKS / RESTRICTION

- Adhesion tests prior to the application are recommended.
- · Avoid contact with water until the adhesive is fully cured.
- Not recommended for PE, PP, Teflon, surfaces permanently wet.
- When bonding polystyrene elements apply the adhesive economically, at long intervals, in thin strips.
- Not recommended for thin polystyrene elements (during curing adhesive can lightly disturb the surface).
- Not suitable for solvent sensitive surfaces.

TECHNICAL DATA

| Color | |
|-------|---|
| beige | + |

| Uncured | Value |
|---|-------------|
| Base: synthetic rubber in organic solvents | + |
| Solid Content [%] | 73 ± 2 |
| Density [g/ml] | 1,25 ± 0,05 |
| Working time (depending on ambient | 10 - 15 |
| conditions and subfloor properties) [min] | |
| Full curing time (in normal conditions) [h] | 72 |
| Yield [g/m2] | 300 - 500 |
| Flammability | + |

| Cured | Value |
|-----------------------------|-----------|
| Temperature resistance [°C] | -20 - +60 |
| Flammability after curing | - |

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on product hardening conditions (c.a., ambient, surface temperature, quality of used equipment and skills of person applying the product).

2014.08.08 - 2 -



Selena FM S.A. ul. Strzegomska 2-4, 53-611 Wrocław, Poland, tel. +48 71 78 38 290, fax: +48 71 78 38 291 e-mail: export@selena.com, www.selenafm.com



TRANSPORT / STORAGE

Warranted shelf life is 12 months from the manufacturing date when stored in unopened, original package at temperatures from +5 °C to +25 °C in a dry place protected from freezing and excessive heat.

SAFETY AND HEALTH PRECAUTIONS

The product is inflammable. All works should be carried out in well-ventilated area away from ignition sources. Do not smoke. The adhesive should be stored in accordance with the rules of storage of inflammable substances. Detailed information is included in the Material Safety Data Sheet (MSDS).

All written or oral information, recommendations and instructions are given according to our best knowledge, tests and experience, in good faith and in compliance with manufacturer's principles. Each user of this material will make sure in every possible way, including verification of the final product in proper conditions, about suitability of the supplied materials for their intended purposes. The manufacturer is not liable for any losses incurred due to inaccurate or erroneous application of the manufacturer's materials.

